
METSÄBOARD NATURAL FBB (UC)





Printing methods

Resistencia

Offset and Flexography















TECHNICAL SPECIFICATIONS			
WEIGHT (g/m²) (ISO 536)	THICKNESS (mm) (ISO 534)	TABER RIGIDITY 15° (mNm) (ISO 2493)	TABER RIGIDITY 15° (mNm)
		DT	DM
175	310	4.0	8.0
190	335	4.8	9.9
200	360	5.7	11.3
210	385	6.8	13.7
225	415	8.3	16.7
235	435	9.2	18.6
245	455	10.2	20.4
260	485	11.8	23.5
270	505	13.2	26.5
295	555	16.2	32.7
325	610	19.2	38.2

PROPIEDADES

SURFACE WHITENESS (C/2º) (ISO 2470-1) (%)

ROBINSON TEST (12 months in original packaging) (EN 1230-2)

Jan-23

The manufacturer of the material reserves the right to make changes without prior notice.