

# DUPLEX BOARD GREY BACK (GD2)



-   
Alimentación
-   
Gráfica
-   
Higiene
-   
Limpieza
-   
Packaging genérico
-   
Productos electrónicos
-   
Sector Industrial

| ESPECIFICACIONES TÉCNICAS   |                           |                                          |                                          |
|-----------------------------|---------------------------|------------------------------------------|------------------------------------------|
| GRAMAJE (g/m²)<br>(ISO 536) | ESPESOR (µm)<br>(ISO 534) | RIGIDEZ TABER 15°<br>(mNm)<br>(ISO 2493) | RIGIDEZ TABER 15°<br>(mNm)<br>(ISO 2493) |
| -                           | -                         | DM                                       | DT                                       |
| 200                         | 240±20                    | 4.2                                      | 2.2                                      |
| 220                         | 265±20                    | 5.4                                      | 2.7                                      |
| 230                         | 275±20                    | 5.9                                      | 2.9                                      |
| 240                         | 285±20                    | 6.4                                      | 3.2                                      |
| 250                         | 305±20                    | 6.9                                      | 3.4                                      |
| 260                         | 315±20                    | 7.4                                      | 3.7                                      |
| 270                         | 340±20                    | 8.8                                      | 4.4                                      |
| 280                         | 355±20                    | 10.8                                     | 5.4                                      |
| 300                         | 385±25                    | 11.8                                     | 5.9                                      |
| 320                         | 410±25                    | 13.7                                     | 6.4                                      |
| 330                         | 425±25                    | 15.2                                     | 6.9                                      |
| 350                         | 455±25                    | 17.7                                     | 8.8                                      |
| 400                         | 520±25                    | 24.5                                     | 12.3                                     |
| 450                         | 590±25                    | 34.3                                     | 17.2                                     |
| 480                         | 630±30                    | 44.1                                     | 22.1                                     |
| TOLERANCIA +/- 5%           |                           |                                          |                                          |

| PROPIEDADES             |      |
|-------------------------|------|
| BLANCURA (ISO 7026) (%) | > 76 |