


CRESCENDO® C1S

Cartulina pasta química estucada una cara con una alta blancura.



Métodos de impresión

Offset
Impresión digital



ESPECIFICACIONES TÉCNICAS			
GRAMAJE (g/m2) (T-410)	ESPESOR (µm) (T-411)	RIGIDEZ TABER 15° (mNm) (ISO 2493)	RIGIDEZ TABER 15° (mNm) (ISO 2493)
-	-	DM	DT
195	254	5.6	2.8
230	305	8.7	4.4
260	345	12.6	6.4
275	376	14.9	7.7
290	406	18.1	9.1
320	452	24.0	12.4
340	493	29.8	15.5
400	597	46.7	23.7

PROPIEDADES	
BLANCURA SUPERFICIE (ISO 2470) (%)	91