DUPLEX BOARD GREY BACK (GD2)

















CARACTÉRISTIQUES TECHNIQUES			
POIDS (g/m2) (ISO 536)	ÉPAISSEUR (μm) (ISO 534)	RIGIDITÉ TABER 15° (mNm) (ISO 2493)	RIGIDITÉ TABER 15° (mNm)
		DT	DM
200	240±20	2.2	4.2
220	265±20	2.7	5.4
230	275±20	2.9	5.9
240	285±20	3.2	6.4
250	305±20	3.4	6.9
260	315±20	3.7	7.4
270	340±20	4.4	8.8
280	355±20	5.4	10.8
300	385±25	5.9	11.8
320	410±25	6.4	13.7
330	425±25	6.9	15.2
350	455±25	8.8	17.7
400	520±25	12.3	24.5
450	ÉPAISSEUR (μm) (ISO 534)	17.2	34.3
480		22.1	44.1
	590±25		
	630±30	-	

PROPIEDADES

BLANCHEUR (ISO 7026) (%)