
METSÄBOARD Pro FBB BRIGHT (GC1)





Métodos de impresión

Offset Impressão digital Flexografía Rotogravura

















ESPECIFICAÇÕES TÉCNICAS				
	GRAMAGEM (g/m2) (ISO 536)	ESPESSURA (μm) (ISO 534)	RIGIDEZ TABER 15° (mNm) (ISO 2493)	RIGIDEZ TABER 15° (mNm)
			DT	DM
	180	260	2.4	5.2
	195	305	3.8	7.8
	220	355	5.4	11.0
	230	385	6.6	13.5
	245	415	8.1	16.5
	255	435	9.0	18.4
	265	455	10.0	20.2
	280	485	11.6	23.3
	290	505	13.0	26.3
	320	555	16.0	32.5
	350	610	19.0	38.0

PROPIEDADES

SUAVIDADE (ISO 8791-4) (pps10)

BRANQUEAMENTO DA SUPERFÍCIE (C/2º) (ISO 2470-1) (%)

BRILHO (HUNTER 75°) (TAPPI 480) (%)

TESTE DE ROBINSON (12 meses na embalagem original) (EN 1230-2)

jan-23