
## METSÄBOARD NATURAL FBB (UC)





## Métodos de impresión

## Resistencia

Offset e Flexografia















ESPECIFICAÇÕES TÉCNICAS			
GRAMAGEM (g/m2) (ISO 536)	ESPESSURA (mm) (ISO 534)	RIGIDEZ TABER 15° (mNm) (ISO 2493)	RIGIDEZ TABER 15° (mNm)
		DT	DM
175	310	4.0	8.0
190	335	4.8	9.9
200	360	5.7	11.3
210	385	6.8	13.7
225	415	8.3	16.7
235	435	9.2	18.6
245	455	10.2	20.4
260	485	11.8	23.5
270	505	13.2	26.5
295	555	16.2	32.7
325	610	19.2	38.2

## **PROPIEDADES**

BRANQUEAMENTO DA SUPERFÍCIE (C/2º) (ISO 2470-1) (%)

TESTE DE ROBINSON (12 meses na embalagem original) (EN 1230-2)

jan-23

O fabricante do material reserva-se o direito de realizar alterações sem aviso prévio.